Corporate Office:
Sangir Plastics P. Ltd. Sangir House,
366/2933, Motilal Nagar II, Mumbai,
India. PIN: 400062.

Manufacturing Unit:
Survey 146 P/23, Behind Raymond
Ltd. Motiwada, Tal: Pardi, Gujarat,
India. PIN: 396125.

Contact:
+91 22 28717800 (30 lines)
22 28724023
e sales@sangir.in

www.sangir.com

TECHNICAL DATA - SHEET OF PVC FLEXIBLE SHEET

Product :- SANGIR-PVC FLEXIBLE TRANSPAREN SHEET(CLEAR)

SANGIR (PALSTNOVA)PVC FLEXIBLE Sheets avaialble in variety of thickness
Regular Sizes: 1 mm to5 mm Or As per customer specific sizes

PROPERTIES OF PRODUCT	STANDARD	Data	Unit
DENSITY	ISO - 1183 / ASTM 1505	≥ 1.30	g/cc
HARDNESS (SHORE-D)	ASTM D 2240	> 70	Shore-A
TENSILE STRENGTH @ YIELD	ISO - 527 / ASTM D 638 Type-IV	≥ 12	Mpa
Elongation at Break	ISO - 527 / ASTM D 638 Type-IV	≥ 150	%

Sangir PVC FLEXIBLE TRANSPAREN Sheets used for service in storage/ Lining of Chemical storage tanks,Shop

The information & data presented herein are typical values and should not be construed as specification. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.